



LOW GLOSS TOPCOAT SILKY FEEL




HIGH CHEMICAL AND
PHYSICAL RESISTANCE

GOOD MAR RESISTANCE

EXCELLENT
LIGHT RESISTANCE

EXTREME
SMOOTHNESS



SILKY FEEL

SAYERLACK
INNOVATIVE WOOD SOLUTIONS



SILKY FEEL

Interior design, following a trend that does not know countertrend, requires extremely opaque surfaces, but enhanced with the refinement of the materials used and exceptional softness to the touch.

Clear opaque acrylic topcoat **TZL3731/00 SILKY FEEL**, designed for the flat parts of furniture, gives matte surfaces, beautiful depth of colour, and a tactile softness which is comparable to that of silk. Opacity becomes warm and touch is soft and natural. **SILKY FEEL** enhances the grain and shades of dark or dark colored wood.

SILKY FEEL combines velvety tone and exceptional softness to touch with excellent surface hardness and high chemical resistances. The soft matte tone is warmed by the effect of the topcoat: clean and minimalist elegance, almost elemental, sophisticated and refined by the tactile experience. The acrylic formula provides excellent resistance to light exposure and significant chemical and physical resistances, even at low angles.

By touching the matte surface finished with **SILKY FEEL**, the skin meets the wood fiber, soft and caressing as silk. A natural but serious elegance, a fundamental and delicate refinement stimulated by tactile effects.

TECHNICAL CHARACTERISTICS OF THE PRODUCT

Product market	Flat panels for furniture
Substrate	Various light and dark, even thermotreated, pre-treated with PE basecoat, acrylic, PU or UV two component
Application	Spray, curtain coater
Hardener	TH0784/00 at 20%
Thinner	DT0090/00 at approx 40%

PRODUCT'S PERFORMANCE

UNI 15187 (assessment of the effect of light exposure): 5
 LEGENDA: 5 "no visible change" and 1 "strong change"
 UNI 10782 (hardness test - pencil method): H

CHEMICAL RESISTANCE

(UNI EN 12720): LEVEL C	Time	Minimum requirement	Result achieved
Acetic acid (10% m/m)	1 h	5	5
Acetone	10 s	4	5
Ammonia (10% m/m)	1 h	4	5
Red wine	1 h	4	5
Citric acid (10% m/m)	1 h	5	5
Detergent solution	16 h	5	5
Coffee	1 h	5	5
Disinfectant	1 h	5	5
Ethyl alcohol (48% V/V)	1 h	4	4
Ethylbutyl acetate (1:1 V/V)	10 s	4	5
Oliv oil	1 h	5	5
Liquid paraffin	1 h	5	5
Sodium carbonate (10% m/m)	1 h	4	5
Sodium chloride (15% m/m)	1 h	5	5
Tea	16 h	5	5
Distilled water	16 h	5	5
Legenda:	0= Very poor 3= Sufficient	1= Poor 4= Good	2= Mediocre 5= Excellent

Technical Service: Ph. +39 051 770770 - Fax +39 051 770521 customerservice@sayerlack.com

Sherwin-Williams Italy S.r.l. - Export Department
 Via del Fiffo 12 - 40065 Pianoro (BO) - Italy
 Ph. +39 051 770511 - Fax +39 051 770528
 export@sayerlack.it - www.sayerlack.com



Sayerlack is a brand of The Sherwin Williams Company