



CLEAR HIGH GLOSS FIRE RETARDANT COATING SYSTEM IN COMPLIANCE WITH BS476 PART 7 CLASS 1



EXCELLENT
BUILDING POWER

EXCELLENT LEVELLING

IN COMPLIANCE WITH
BRITISH STANDARD
BS476 PART 7 CLASS 1

FIRST-CLASS
PROTECTION

CLEAR HIGH GLOSS FIRE RETARDANT COATING SYSTEM

IN COMPLIANCE WITH BS476 PART 7 CLASS 1

Sayerlack achieves the first-class protection for high gloss and clear design.

| COATING SYSTEM | | g/m ² | TOTAL g/m ² | SUBSTRATE | STANDARD | CLASS |
|----------------|--|------------------------|------------------------|-----------|-----------------|-------|
| TU0565/00 | +50% DT1150/00 + 100% TH0765/00 | 1x100 g/m ² | 720 g/m ² | MDF | UK BS476 part 7 | 1 |
| PU4101/00 | +50% PX4102/00 + 3% PH0777/00 + 3% PH0888/00 | 2x250 g/m ² | | | | |
| TL4100/00 | +100% TH0735/00 + 5% DT0441/00 | 1x120 g/m ² | | | | |

A certified fire retardant coating system, tested according to **British Standard BS476 part 7**, which fulfills the requirements of **class 1**.

The combination of a polyurethane sealer, a red-ox polyester basecoat and an acrylic topcoat make of this new coating system the proper solution to confer fire retardant properties to flat substrates and furniture, giving an extremely high build and high gloss appearance, maintaining visible the natural vein of the wood.

| | | |
|-----------------------|-----------------------|--|
| Application | By spray | |
| Product market | Flat parts, furniture | |
| Substrate | Sanded wood | |
| Drying time | Primer TU0565/00 | Dust free: 10' Touch dry: 3h Sandable: 12h Stackable: 12h |
| | Basecoat PU4101/00 | Dust free: 40' Touch dry: 1h Sandable: 24h Stackable: 12h |
| | Topcoat TL4100/00 | Dust free: 40' Touch dry: 3h Sandable: 3-4 days Stackable: 24-48h |

Performance should be certified on particular substrate depending on end use. For more information, please contact your local Sayerlack representative.

Technical Service: Ph. +39 051 770770 - Fax +39 051 770521 customerservice@sayerlack.com

Sherwin-Williams UK Coatings Ltd.

A1 Business Park, Knottingley, West Yorkshire - WF11 OBU, England
Ph. +44 (0) 1977 673363 - Fax +44 (0) 1977 673521
ukinfo@sherwin.com - www.sayerlack.co.uk

Sherwin-Williams Ireland Ltd.

53 Robinhood Industrial Estate - Dublin 22, Ireland
Ph. +353 1460 1445 - Fax +353 1460 1449
irlinfo@sherwin.com - www.sayerlack.co.uk

Sherwin-Williams Italy S.r.l. - Export Department

Via del Fiffo 12 - 40065 Pianoro (BO) - Italia
Ph. +39 051 770511 - Fax +39 051 770528
export@sayerlack.it - www.sayerlack.com



Sayerlack is a brand of The Sherwin Williams Company