



# HYDROPLUS WHITE WATERBORNE TOPCOAT FOR INTERIORS

READY TO USE

50 GLOSS

HIGH ELASTICITY

ATL3401/13





# HYDROPLUS WHITE WB TOPCOAT FOR INTERIORS ATL3401/13

The peculiar formula of **ATL3401/13** allows its use when drying temperatures exceed 45°C. In addition, the special resin system imparts high elasticity and makes it suitable for IR and forced air drying in just 40-60 seconds after the application. In these conditions, drying and stackability are much faster than to the other waterborne coatings.

<b>AREA OF USE</b>	MDF and interior doors
<b>METHOD OF USE</b>	Spray: conventional, air mix, airless, electrostatic
<b>THINNING</b>	Ready to use. If thinning is required, use tap water up to 5%

To improve the chemical resistance, surface hardness and scratch resistance, it is possible to add slowly and under stirring conditions 1% of **XA4080/00**, the crosslinker for waterborne coatings.

<b>TECHNICAL CHARACTERISTICS</b>	
<b>SOLID CONTENT (%)</b>	41 ± 2
<b>SPECIFIC GRAVITY</b>	1.150 ± 0.030
<b>VISCOSITY (DIN 4 at 20°C)</b>	120" ± 5"
<b>APPLICATION WEIGHT (g/m<sup>2</sup>)</b>	80 ± 120

Technical Service: Ph. +39 051 770770 - Fax +39 051 770521 [customerservice@sayerlack.com](mailto:customerservice@sayerlack.com)

**Sherwin-Williams Italy S.r.l. - Export Department**  
Via del Fiffo 12 - 40065 Pianoro (BO) - Italia  
Ph. +39 051 770511 - Fax +39 051 770528  
[export@sayerlack.it](mailto:export@sayerlack.it) - [www.sayerlack.com](http://www.sayerlack.com)



Sayerlack is a brand of The Sherwin Williams Company